

# DAMAR MINYAK

*Agathis Dammara, Agathis Borneensis*



www.brittontimbers.com.au



## Description

Heartwood pale yellowish brown, sometimes with a pinkish tinge. Sapwood often hard to distinguish from the heartwood.

Texture very fine and even. Grain straight. No figure. Free of brittleheart.

*Also known as East Indian Kauri, Indonesian Kauri.*

## Suitability

- ✓ Boating
- ✓ Cabinet Door
- ✓ Decking & Cladding
- ✓ Flooring & Staircase
- ✓ Furniture
- ✓ Joinery

## TECHNICAL INFORMATION

Density (kg/m <sup>3</sup> dry)	550	Hardness (Janka) (kN)	3	Resistance to Split in Nailing	Excellent
Specific Gravity	0.5	Finish	Excellent	Resistance to Split in Screwing	Excellent
Modulus of Rupture (MPa dry)	67	Stability	Good	Gluing	Good
Modulus of Elasticity (GPa dry)	12	Durable	No	Growing Region	Asia Pacific
Radial Shrinkage %	1.5	Sapwood Lyctid Susceptible	No	Availability	Widely
Tangential Shrinkage %	3	Machining	Excellent		

### New South Wales

116-118 Jemma Rd  
Prestons NSW 2170

☎ 02 8783 9900

### Victoria

25 Gaine Rd  
Dandenong VIC 3175

☎ 03 8769 7111

### Queensland

29 Sodium St  
Narangba QLD 4504

☎ 07 3888 3351

### Tasmania

3 Brittons Rd  
Smithton TAS 7330

☎ 03 6452 2522