


DURIAN

Durio, Neesia, Coelostegia Spp



Description

Sapwood is only moderately well defined in Coelostegia but well defined in Durio and Neesia.

Heartwood is pink brown, grey brown, brown with a red tinge or light orange brown.

Grain is straight to slightly interlocked. Texture is moderately coarse and even in Neesia but uneven in Durio and Coelostegia.

Suitability

- ✘ Boating
- ✓ Cabinet Door
- ✘ Decking & Cladding
- ✓ Flooring & Staircase
- ✓ Furniture
- ✓ Joinery

TECHNICAL INFORMATION

Density (kg/m ³ dry)	650	Hardness (Janka) (kN)	6	Resistance to Split in Nailing	Good
Specific Gravity	0.65	Finish	Good	Resistance to Split in Screwing	Fair
Modulus of Rupture (MPa dry)	95	Stability	Good	Gluing	Fair
Modulus of Elasticity (GPa dry)	16	Durable	No	Growing Region	Asia Pacific
Radial Shrinkage %	2.5	Sapwood Lyctid Susceptible	Yes	Availability	Available
Tangential Shrinkage %	4	Machining	Good		

New South Wales

116-118 Jemma Rd
Prestons NSW 2170

☎ 02 8783 9900

Victoria

25 Gaine Rd
Dandenong VIC 3175

☎ 03 8769 7111

Queensland

29 Sodium St
Narangba QLD 4504

☎ 07 3888 3351

Tasmania

3 Brittons Rd
Smithton TAS 7330

☎ 03 6452 2522