


JARRAH

Eucalyptus Marginata



Description

Heartwood is a rich dark brownish red, sometimes marked by short, dark brown radial flecks on the end grain and boat shaped flecks on flat sawn surfaces which enhance it's decorative value.

The grain is usually straight but often interlocked or wavy. The texture is even but moderately coarse.

Also known as Western Australian Jarrah.

Suitability

- ✓ Boating
- ✓ Cabinet Door
- ✓ Decking & Cladding
- ✓ Flooring & Staircase
- ✓ Furniture
- ✓ Joinery

TECHNICAL INFORMATION

Density (kg/m ³ dry)	820	Hardness (Janka) (kN)	8.5	Resistance to Split in Nailing	Fair
Specific Gravity	0.8	Finish	Good	Resistance to Split in Screwing	Fair
Modulus of Rupture (MPa dry)	112	Stability	Good	Gluing	Good
Modulus of Elasticity (GPa dry)	13	Durable	Yes	Growing Region	WA
Radial Shrinkage %	5	Sapwood Lyctid Susceptible	Yes	Availability	Widely
Tangential Shrinkage %	8	Machining	Fair		

New South Wales

116-118 Jemma Rd
Prestons NSW 2170

☎ 02 8783 9900

Victoria

25 Gaine Rd
Dandenong VIC 3175

☎ 03 8769 7111

Queensland

29 Sodium St
Narangba QLD 4504

☎ 07 3888 3351

Tasmania

3 Brittons Rd
Smithton TAS 7330

☎ 03 6452 2522