



Description

Sapwood is moderately well defined. Heartwood is brown with a red or pink tinge or red brown.

Grain is shallow to deeply interlocked. Texture is moderately fine and even.

Suitability

- ✘ Boating
- ✓ Cabinet Door
- ✓ Flooring & Staircase
- ✓ Furniture
- ✓ Joinery

TECHNICAL INFORMATION

| | | | | | |
|---------------------------------|------|----------------------------|------|---------------------------------|--------------|
| Density (kg/m ³ dry) | 755 | Hardness (Janka) (kN) | 7 | Resistance to Split in Nailing | Good |
| Specific Gravity | 0.75 | Finish | Good | Resistance to Split in Screwing | Good |
| Modulus of Rupture (MPa dry) | 85 | Stability | Good | Gluing | Fair |
| Modulus of Elasticity (GPa dry) | 12 | Durable | Yes | Growing Region | Asia Pacific |
| Radial Shrinkage % | 1.4 | Sapwood Lyctid Susceptible | No | Availability | Available |
| Tangential Shrinkage % | 2.5 | Machining | Fair | | |

New South Wales

116-118 Jemma Rd
Prestons NSW 2170

☎ 02 8783 9900

Victoria

25 Gaine Rd
Dandenong VIC 3175

☎ 03 8769 7111

Queensland

29 Sodium St
Narangba QLD 4504

☎ 07 3888 3351

Tasmania

3 Brittons Rd
Smithton TAS 7330

☎ 03 6452 2522