



Description

Heartwood reddish brown. Sapwood narrow, pale red and distinctive.

Texture moderately coarse. Grain often interlocked.

Characteristic cedar odour. The wood is very similar to that of Australian red cedar.

Also known as Kalantas, Red Cedar.

Suitability

- ✗ Boating
- ✗ Cabinet Door
- ✗ Decking & Cladding
- ✗ Flooring & Staircase
- ✗ Furniture
- ✓ Joinery

TECHNICAL INFORMATION

Density (kg/m ³ dry)	480	Hardness (Janka) (kN)	2	Resistance to Split in Nailing	Good
Specific Gravity	0.45	Finish	Excellent	Resistance to Split in Screwing	Good
Modulus of Rupture (MPa dry)	65	Stability	Good	Gluing	Fair
Modulus of Elasticity (GPa dry)	8	Durable	Yes	Growing Region	Asia Pacific
Radial Shrinkage %	4	Sapwood Lyctid Susceptible	Yes	Availability	Available
Tangential Shrinkage %	7	Machining	Good		